

310 A BASIC




LLDPE cast stretch film for wrapping machines without prestretch group where no special needs are required.

Characteristic	Method	Unit	Direction	23 µm	Tolerances
Impact resistance	ASTM D1709 A	g	-	80	10%
Tensile strength at break	ASTM D882 B	MPa	Machine Direction	27	10%
			Transversal Direction	20	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine Direction	6	10%
			Transversal Direction	5	10%
Elongation at break	ASTM D882 B	%	Machine Direction	450	10%
			Transversal Direction	550	10%
Tear Resistance	ASTM D1922	mN	Machine Direction	1731	10%
			Transversal Direction	2708	10%
Stretch	Hipac	%	-	125	5%
Cling	Hipac	g	-	130	10%

Coloured	Slippery	AUV 6/12 months	Antistatic	Net Roll	Cling Out/In/Both	Low Temperature	Printed	Double Edges
✘	✘	✘	✘	✘	✘	✘	✘	✘

HIPAC STRETCH FILM HAS BEEN
DESIGNED TO BE 100% RECYCLABLE



The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.