

# 555 A/M RIGID



LLDPE cast stretch film, suitable for **wrapping machines without prestretch group and for hand wrap**. Thickness downgauging maintaining the same performance allows 555 to replace any kind of standard film saving up to 50% material.


Characteristic	Method	Unit	Direction	12 µm	Tolerances
Impact resistance	ASTM D1709 A	g	-	79	10%
Tensile strength at break	ASTM D882 B	MPa	Machine Direction	30	10%
			Transversal Direction	17	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine Direction	15	10%
			Transversal Direction	4.2	10%
Elongation at break	ASTM D882 B	%	Machine Direction	310	10%
			Transversal Direction	558	10%
Tear Resistance	ASTM D1922	mN	Machine Direction	280	10%
			Transversal Direction	3200	10%
Stretch	Hipac	%	-	100	5%
Cling	Hipac	g	-	135	10%

In case of coloured stretch film these values should be reduced by 10%.

In case of additives these values should be reduced by 5%.

In case of printed film these values should be reduced by 5%.

Coloured	Slippery	AUV 6/12 months	Antistatic	Net Roll	Cling Out/In/Both	Low Temperature	Printed	Double Edges
								



The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.