

HIPAC Group 112 A SUPER POWER PLUS



Hipac LLDPE cast stretch film, specially designed to achieve extremely high prestretch in very low thickness. To be used on wrapping machines WITH prestretch group.

Characteristic	Method	Unit	Direction	15 μm	Tolerances
Impact resistance	ASTM D1709 A	g	-	184	10%
Tensile strength at break	ASTM D882 B	MPa	Machine Direction	32	10%
			<b>Transversal Direction</b>	28	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine Direction	8,5	10%
			<b>Transversal Direction</b>	7,5	10%
Elongation at break	ASTM D882 B	%	Machine Direction	605	10%
			<b>Transversal Direction</b>	750	10%
Tear Resistance	ASTM D1922	mN	Machine Direction	2630	10%
			<b>Transversal Direction</b>	4150	10%
Prestretch*	Hipac	%	-	330	5%
Cling	Hipac	g	-	125	10%

\* Intended as the sum of prestretch and post-stretch (lay on tension).

In case of additives these values should be reduced by 5%.

In case of printed film these values should be reduced by 5%.

Coloured	Slippery	AUV 6/12 months	Antistatic	Net Roll	Cling Out/In/Both	Low Temperature	Printed	Double Edges
×	<b>V</b>	$\checkmark$	1	<b>V</b>	1	<b>V</b>	$\checkmark$	<b>V</b>
HIPAC STRETCH FILM HAS BE DESIGNED TO BE 100% RECY								

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.