

## **E801 - ECOSTRETCH FILM**





Ecostretch is a LLDPE cast coextruded stretch film, especially designed for the wrapping of the bales of waste. Storage, often outdoors, requires a film with high mechanical strength and resistant to UV and atmospheric agents.

Characteristic	Method	Unit	Direction	25 μm	30 μm	Tolerances
Impact resistance	<b>ASTM D1709 A</b>	g	-	154	165	10%
Tourile strongth at break	ASTM D882 B	MPa	Machine Direction	35	36	10%
Tensile strength at break	ASTIVI DOOZ B	IVIPa	Transversal Direction 20	21	10%	
Tanaila atuanath at viald	ASTM D882 B	МРа	Machine Direction	8	8	10%
Tensile strength at yield	ASTIVI DOOZ B		Transversal Direction	6	6	10%
Element and head	ASTM D882 B	0/	<b>Machine Direction</b>	583	610	10%
Elongation at break	ASTIVI D882 B	70	% Transversal Direction	690	710	10%
Tear Resistance	ASTM D1922	mN	<b>Machine Direction</b>	3601	4039	10%
			<b>Transversal Direction</b>	4326	5172	10%
Cling	Hipac	g	-	135	135	10%

Stretch GARANTED	AUV 6/12 months GARANTED	Coloured*	Net Roll (coreless)	
70-100%	<b>√</b>	WHITE/BLACK	<b>V</b>	







<sup>\*</sup> Other colours are available on customer's request



The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.

Visit us at www.hipac.com Release 2025



## E301 - ECOSTRETCH FILM





Ecostretch is a LLDPE cast coextruded stretch film, especially designed for the wrapping of the bales of waste. Storage, often outdoors, requires a film with high mechanical strength and resistant to UV and atmospheric agents.

Characteristic	Method	Unit	Direction	25 μm	30 μm	Tolerances
Impact resistance	<b>ASTM D1709 A</b>	g	-	138	149	10%
Tanaila atuamath at busali	ASTM D882 B	MPa	<b>Machine Direction</b>	35	36	10%
Tensile strength at break	ASTIVI DOOZ B	IVIPa	Transversal Direction	20	21	10%
Tanaila atuanath at viald	ASTM D882 B	MPa	<b>Machine Direction</b>	8	8	10%
Tensile strength at yield	ASTIVI DOOZ B		Transversal Direction	6	7	10%
Florestian at bussle	ASTM D882 B	%	Machine Direction	528	605	10%
Elongation at break	ASTIVI DOOZ B	70	Transversal Direction 680	680	700	10%
Tear Resistance	ASTM D1922	mN	<b>Machine Direction</b>	3228	3641	10%
			<b>Transversal Direction</b>	3907	4620	10%
Cling	Hipac	g	-	135	135	10%

Stretch GARANTED	AUV 6/12 months GARANTED	Coloured*	Net Roll (coreless)
70-100%	<b>√</b>	WHITE/BLACK	<b>√</b>







<sup>\*</sup> Other colours are available on customer's request



The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.

Visit us at www.hipac.com Release 2025