TECHNICAL SPECIFICATIONS

5-10-2026 rel.30

General Tolerance except Prestretched film.

Internal Ø (mm)	Core length (mm)	Core weight (g)	Film Thickness (µ)	** Film width (mm) [a]	Film length	Core weight	Internal Core Ø (mm)	Core length (mm)	Reel weight
50	520	200/300	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±7%	±1,5	+6 -3	±5%
50	520	500	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±10%	±1,5	+6 -3	±5%
50	520	600/700/800	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±9%/±8%/±7%	±1,5	+6 -3	±5%
50	470	180/270/450	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	± 7%	±1,5	+6 -3	±5%
50	260	220	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±7%	±1,5	+6 -3	±5%
50	73/153/128/103	128/267/224/180	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±3	±5%	±7%	±1,5	+6 -3	±5%
38	140/128/103	85/75/60	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±3	±5%	±8%	±1,5	+3 -2	±5%
38 R[b]	103/128/260	89/110/220	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±3	±5%	±7%	±1,5	+3 -2	±5%
76	520[c]	850	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±5%	±1,5	+6 -3	±5%
76	510/510/1.010	1.000/1.700/3.367	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±5%	±1,5	+6 -3	±5%
76	385/510/760	1.283/1.800/2.550	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±5%	±1,5	+6 -3	±5%
76	1.260	4.200	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±5%	±1,5	+6 -3	±5%
76[d]	510	1.860	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±5%	±1,5	+6 -3	±5%
76	510	1.950	23-35 ±2	±8	±5%	±7%	±1,5	+6 -3	±5%
76	255/128/103	850/427/333	7-23 ±1 - 24-35 ±2 – 36-80 ±3	±8	±5%	±5%	±1,5	+6 -3	±5%

[a] During the first 20 meters of the coil ±25 mm. In case of reinforced edges the value of 8mm will be of 15mm.
[b] Reinforced core.
[c] To be used only in 5Kg total reel weight.
[d] Plastic core. To be used only for printed Films. Non-returnable plastic core.

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.

HIPAC SpA: Via per Rovato, 10 25046 Cazzago S. Martino (Brescia) – **ITALY** Phone: +39 030 7750610 Fax:+39 030 7750847.
IBERHIPAC SA: Crta N-V Km 189,1 10390 Saucedilla (Cáceres) - **SPAIN** Phone: +34 927 545188 Fax:+34 927 545187.
HIPAC ROMANIA srl: Dragomiresti Vale, Ilfov (Bucuresti) – **ROMANIA** Phone: +40 21 3523600 Fax:+40 21 3523608.

Visit us at www.hipac.com

TECHNICAL SPECIFICATIONS

5-10-2026 rel.30

Prestretched film Tolerance.

Internal Ø (mm)	Core length	Film Thickness (µ)	Film width (mm)	Film length	Core weight	Internal Core Ø (mm)	Core length (mm)	Reel weight
76	**460 mm weight 1,533 Kg**	±1	±10	±7%	±5%	±1,5	+6 -3	± 7%
50	**470 mm weight 0,27 Kg**	±1	±10	±7%	±7%	±1,5	+6 -3	± 7%
50	**470 mm weight 0,45 Kg**	±1	±10	±7%	±7%	±1,5	+6 -3	± 7%

"Sun light Resistance" for printed film.

June-July-August	September-April-May	October-November-March	December-January-February
40 days	120 days	240 days	720 days

- The above mentioned values (tested with instrument XENOTEST 150 S) are considered with the sun light in the range of the Washington meridian; Exposure from 9:00 to 15:00.
- Although HIPAC uses colours with "Light Resistance" index 7 for printing but due to the fact that the film can be exposed under innumerable situations which mean uncontrolled solar radiation quantities absorbed, HIPAC does not guarantee the duration and appearance of the printing in printed films.

Printed film Tolerance.

For printed films the printing width and/or height can vary, depending on the thickness, by 5%.

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.

HIPAC SpA: Via per Rovato, 10 25046 Cazzago S. Martino (Brescia) – **ITALY** Phone: +39 030 7750610 Fax:+39 030 7750847.
IBERHIPAC SA: Crta N-V Km 189,1 10390 Saucedilla (Cáceres) - **SPAIN** Phone: +34 927 545188 Fax:+34 927 545187.
HIPAC ROMANIA srl: Dragomiresti Vale, Ilfov (Bucuresti) – **ROMANIA** Phone: +40 21 3523600 Fax:+40 21 3523608.

Visit us at www.hipac.com

TECHNICAL SPECIFICATIONS

5-10-2026 rel.30

NETROLL film tolerances (Prestretched and non Prestretched film)

Roll type	Film Thickness (µ)	Film width (mm)	Film length	Roll type	Internal Core Ø (mm)	Reel weight
Automatic	9-23 ±1 - 24-35 ±2	±8	±5%	Automatic	74±4	±5%
Manual	9-23 ±1 - 24-35 ±2	±8	±5%	Manual	45±5	±5%

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.

HIPAC SpA: Via per Rovato, 10 25046 Cazzago S. Martino (Brescia) – **ITALY** Phone: +39 030 7750610 Fax:+39 030 7750847.
IBERHIPAC SA: Crta N-V Km 189,1 10390 Saucedilla (Cáceres) - **SPAIN** Phone: +34 927 545188 Fax:+34 927 545187.
HIPAC ROMANIA srl: Dragomiresti Vale, Ilfov (Bucuresti) – **ROMANIA** Phone: +40 21 3523600 Fax:+40 21 3523608.

Visit us at www.hipac.com